

ARDEX K 60™

Rapid Setting Latex Smoothing and Leveling Compound

Choose Versatile, No Water - ARDEX K 60™ ARDITEX offers unmatched flexibility and adhesion. Use on permanently wet areas prior to installing ARDEX MC™ Moisture Control Systems. Contact the ARDEX Technical Service department for a jobsite recommendation.

Install over: interior concrete, terrazzo, ceramic and quarry tile, steel, select epoxy coating systems and non-water-soluble adhesive residue on concrete

Key Features

- No mechanical profiling required in most applications
- No priming required in most applications
- No water required
- Portland cement and other hydraulic cements
- Self-smoothing, trowelable
- Latex leveling compound
- Interior use
- Use on, above or below grade

Installation

- **General priming recommendations:** When required
- **Packaging:** 35 lb. (15.9 kg) w, 1 Gallon (3.8 L) bottle
- **Coverage:** 21 sq. ft. per bag at 1/4" (1.95 m² at 6 mm)
- **Thickness:**
 - Levels at 1/8" (3 mm)
 - Installs from 1/16" to 1/2" (1.5 mm to 12 mm)
 - Featheredge to match existing elevations
- **Flow time:** 10 minutes
- **Walkable:** 2 to 3 hours
- **Install floor coverings:**
 - **Moisture insensitive tiles:** 6 hours
 - **Porous-backed carpet:** 12 hours
 - **Other flooring:** 16 to 24 hours

Performance

- **ASTM C191 Initial Set:** Approx. 30 minutes
- **ASTM C191 Final Set:** Approx. 60 minutes
- **Compressive Strength (ASTM C109 Modified):** 3,500 psi (246 kg/cm²) at 28 days
- **ASTM E10 modified Brinell Hardness:** Approx. 2,900 psi (203 kg/cm²) at 24 hours
- **VOC:** 0



For easy-to-use ARDEX Product Calculators and Product Information On the Go, download the ARDEX App at the iTunes Store or Google play.



Refer to the technical data sheet at www.ardexamericas.com or call 888-512-7339 prior to installation. For free ARDEX product training, click on ARDEX Academy.

AF372 10/15

SUBSTRATE
PREPARATION

CHOOSE
YOUR
SOLUTION



AMERICAS

888-512-7339

+1-724-203-5000

www.ardexamericas.com